




**SAMPLE DYNAMOMETER
SCHEDULE B8E4-73 (S.A.E. J661a)**



| Result Summary | | | | | | | | | |
|----------------|--------------|-------------|-------------|-------------------|------------------|---------------|---------------|-------------|------------|
| Test number | Material | Wear weight | Micro wear | Total weight loss | Toal weight wear | μ -normal | Rating normal | μ -hot | Rating hot |
| CM7613 | LAMCO CD1906 | 0.33 | 0.36 | 0.66 | 1.28 | 0.47 | G | 0.51 | G |
| CM7614 | LAMCO CD1906 | 0.34 | 0.38 | 0.66 | 1.27 | 0.47 | G | 0.52 | G |
| CM7615 | LAMCO CD1906 | 0.33 | 0.36 | 0.64 | 1.28 | 0.47 | G | 0.52 | G |
| AVERAGE | | 0.33 | 0.37 | 0.65 | 1.28 | 0.47 | G | 0.52 | G |